

### **Specifications of 20-30 bitumen**

<b>TEST</b>	<b>Unit</b>	<b>Test method</b>	<b>Grade</b>
<b>Penetration at 25 °C</b>	<b>0.1mm</b>	<b>EN 1426</b>	<b>20-30</b>
<b>Softening Point</b>	<b>°C</b>	<b>EN 1427</b>	<b>55-63</b>
<b>Resistance to Hardening at 163 °C</b>		<b>EN 12607-1 or EN 12607-3</b>	
<b>Change of Mass Maximum</b>	<b>%</b>		<b>0.5</b>
<b>Retained Penetration Minimum</b>	<b>%</b>		<b>55</b>
<b>Softening Point after Hardening Minimum</b>	<b>°C</b>	<b>EN 1427</b>	<b>57</b>
<b>Flash Point Minimum</b>	<b>°C</b>	<b>EN 22592</b>	<b>240</b>
<b>Solubility Minimum</b>	<b>%(m/m)</b>	<b>EN 12592</b>	<b>99.0</b>