

No.	Test	Standard Range		Test Method	
		Min	Max	INSO	ASTM
1	Specific Gravity 25°C/25°C	1.01	1.05	3872	D70
2	Penetration 25°C-100gr-5s,0.1mm	200	300	2950	D5
3	Softening Point°C(R&B)	32	-	3868	D36
4	Flash Point°C (Cleveland Open Cup)	175	-	198	D92
5	Ductility 25°C 5cm/min, cm	100	-	3866	D113
6	Solubility In Trichloroethylene (wt)%	99.0	-	2953	D2042
7	Spot Test	Negative		2949	AASHTO T102
8	Kinematic Viscosity 135°C,mm ² /s	-	-	12855	D2170
9	Dynamic Viscosity 60°C, Pa.s	-	-	12851	D2171
10	Penetration Index	-1.5	+0.7	-	EN 12607-1